

VibroPressed Slab SRI Values

Hemispherical Spectral Reflectance and Total Emittance Test Report

Manhattan Natural	
% Solar Reflectance	SRI
17.0	15

Manhattan Sierra Beige	
% Solar Reflectance	SRI
25.8	26

Manhattan Pearl White	
% Solar Reflectance	SRI
40.4	46

Hampton Natural	
% Solar Reflectance	SRI
21.3	20

Manhattan Charcoal	
% Solar Reflectance	SRI
9.6	6

Hampton Charcoal	
% Solar Reflectance	SRI
13	11

Manhattan Espresso	
% Solar Reflectance	SRI
14.5	13

Hampton Pearl White	
% Solar Reflectance	SRI
37.8	42

Manhattan Winter Sky	
% Solar Reflectance	SRI
12.2	10

The Solar Reflectance Index is calculated from ASTM E1980.